



Blister Base

**RUTLAND**  
PLASTIC TECHNOLOGIES, INC.



# Blister Base Print Instructions

1. **Ink** : MP0231 Bister Base mixed with CB's to achieve blue.

**Mesh** : 83 in / 32 cm (400 capillary film)

**Squeegee** : 60

**\*\* FLASH \*\***

2. **Ink** : MP0231 Bister Base mixed with CB's to achieve blue.

**Mesh** : 83 in / 32 cm (400 capillary film)

**Squeegee** : 60

Cure at 320 - 340 degrees F / 160-171degrees C  
Higher temperatures and longer dwell times in the dryer  
will create a higher, more blistered texture.