

Claira Shatter Base & Foil



# Claira Shatter Base/Foil Print Instructions

1.



**Ink:** ES0246 NPT Shatter Base mixed with 10%  
EB Conc. ( PMS 429 C Grey)

**Mesh:** 110 in / 43 cm

**Squeegee:** 60/90/60

**\*\* FLASH \*\***

2.



**Ink:** ES0246 NPT Shatter Base mixed with 10%  
EB Conc. ( PMS 429 C Grey)

**Mesh:** 110 in / 43 cm

**Squeegee:** 60/90/60

- Cure at 350 degrees F/176 C
- Apply foil on a heat transfer press at 350 - 375 degrees F/176 -190 C at 40 psi /
- Allow print to cool and then pull on image to achieve a cracked print.