



Plastic Technologies, Inc.

www.rutlandinc.com



1.



Ink : ES0840 S.H.A.P.E. mixed with 15% EM8394 Black.

Mesh : 305 in / 120 cm

Squeegee : 70/90/70

2.



Ink : ES0247 Soft Density Base mixed with 10% EB's to achieve 466 C Tan.

Mesh : 83 in / 32 cm

Squeegee : 60/90/60

**** FLASH ****

3.



Ink : ES0840 S.H.A.P.E. mixed with 50% EM8394 Black.

Mesh : 305 in / 120 cm

Squeegee : 70/90/70

4.



Ink : SE0861 NPT Sand Paper Base ink.

Mesh : 24 in / 9.5 cm

Squeegee : 60/90/60

**** FLASH ****

5.



Ink : SE3246 NPT Sand Paper Detail ink.

Mesh : 255 in / 100 cm

Squeegee : 70/90/70

Cure at 320 degrees F / 160 C